

# ANTICORRay Primer 720

## CORROSION PROTECTION

### STRUCTURE

**Solids:**

Butyl rubber and hydrocarbon resin.

**Solvent:**

Petroleum spirit.

**Colour:** black.

**UFI:** E800-F0TW-V005-TSXM

### TECHNICAL DATA

Parametrs	Unit	Value
Solid parts	%	20
Density (in 20°C)	kg/dm <sup>3</sup>	0.76
Flash point	°C	-12
Coverage rate	l/ m <sup>2</sup>	0.2



ANTICOR Sp. z o.o. holds the ISO 9001:2015 certificate.

### ANTICORRay Primer 720

Corrosion protection primer in class C and B steel surface protection systems, according to EN 12068.

### RECOMMENDED USE / DESIGNED FOR

- Basic layer of corrosion protection in multi-layer tape systems, applied to the cleaned steel surface.
- Temporary corrosion protection of pipelines, steel tanks and fittings.

### FEATURES AND ADVANTAGES

- Effectively protects steel surfaces against the effects of factors initiating corrosion processes.
- Contains Stress Corrosion Cracking inhibitors (SCC).
- Possess very good penetrating properties.
- Increases adhesion of coating to the protected steel surfaces.

### APPLICATION

- Before applying the primer, condition the primer at the temperature above 15°C and mix thoroughly before use (do not dilute!).
- Apply the primer on prepared surface to the cleanliness degree Sa 2½ (according to ISO 8501). In justified cases, it is allowed to prepare the surface to the degree of cleanliness St3 (mechanically, using steel rotating brushes).
- Apply a thin layer with a brush, brush, sponge, or spray. Do not use naked flames during application - primer and vapors are flammable!

### STORAGE

- Store the product in dry area in original packaging.
- Protect the cartons against mechanical damage.
- The recommended storage temperature: up to 25°C.

### PRODUCT FORM & SIZE AVAILABLE

Can: 1 litre.